

Type

Uula Boat Varnish is a traditional oil varnish made of boiled linseed oil (varnish) and natural resins.

Intended use

For exterior use on new and old wood surfaces, e.g. boats and garden furniture, also well suited for interior varnishing, e.g. doors, floors, window frames etc.

Technical qualities

Gloss grade: Glossy.

Density approx. 0.98 kg/L.

Aromatic-free hydrocarbon solvent.

Contains: VOC max. 400 g/L.

EU VOC-limit value: (cat A/e) 400g/L (2010).

Colours

Clear, slightly amber.

Application & Conditions

Varnish brush or spatula.

The surface to be painted must be dry, the wood having a moisture content below 15 %. The relative air humidity must be below 80 % and the temperature at least +15°C. Do not varnish in direct sunlight.

Drying time

Dust-dry in approximately four hours. A new coat can be applied after 24 hours at the earliest. (+20°C and the relative air humidity below 80%)

Note: Heat and light accelerate drying.

Coverage

12–20 m²/L.

Thinner

Uula Universal Thinner

Container sizes

1 L, 3 L and 10 L.

Cleaning of equipment

Clean the equipment with Uula Universal Thinner or petroleum spirit and rinse with soap and water.

Storage & disposal

Keep out of the reach of children. Does not freeze.

Dry and empty containers can be taken to a refuse dump.

Liquid waste must be taken to a municipal hazardous waste collection point.

Fire classification

Non-flammable.

Caution: Linseed oil on cleaning rags etc. may catch fire by itself. Oily rags and cloths etc. should be burned or rinsed in water before putting into refuse bins.

Painting instructions

Preparations

Wash dirty surfaces with Uula Washing Agent, mouldy surfaces with Uula Mould Cleaning Agent. In exterior use, treat the surfaces with Uula Anti-Mould Agent according to instructions and let dry thoroughly. Remove peeling old varnish from previously varnished surfaces with an iron or metal scraper. (in both interiors & exteriors), sand and remove dust.

Undercoat

Apply 1–2 thin layers of Boat Varnish. Sand in between and remove dust.

Finishing

Apply 2–3 coats Uula Boat Varnish onto the surface, depending on the intended use. Sand the surface lightly in between and remove the dust.

Thin with Uula Universal Thinner if necessary.

Note: Too thick a layer of varnish wrinkles and dries extremely slowly.

Points to note

*To make the varnish easier to be applied, warm it in a water bath.

Should the varnish become too thick, thin it with Uula Universal Thinner.

(This is especially important when painting in cool conditions, e.g. 5–10°C)

*It is particularly important to apply the varnish thinly on floors.

*In case of uncertainty, submit to the manufacturer of the paint or to a competent distributor before starting the painting process.

Information in the technical specification is based on tests and practical experience. All instructions are only indicative and depend, for example, on the texture of the surface, quality, colour and previous treatments. Because we cannot control the use and working conditions of our products we take responsibility only for the quality of the product and guarantee that it is in accordance with the high standards of Uulatuote Oy. We do not take responsibility for damage caused by using the product against our instructions or intended use.