

Type

Traditional wood oil for exterior use. Made of boiled linseed oil.
Protects the wood from damp and also reduces cracking of the wooden surface.

Intended use

New and old untreated wooden surfaces and also old exterior wooden surfaces previously impregnated or pressure treated with agents that do not form a hard coating, e.g. log and board surfaces, wood stairs, jetties, window frames etc.

The surface can also be impregnated by immersion impregnation.

Technical qualities

Density approx. 0.85 kg/L.

VOC emissions max 700g/l

EU VOC -limit value: (cat A/d) 700g/L (2010).

Colours

See Uula Colour Chart translucent colours.

Uula Wood Oil is tinted with colour pastes made from genuine colour pigments.

Application & conditions

Ordinary paint brush, small brush or immersion.

The surface must be dry and the moisture content of the wood below 15 %.

The relative air humidity must be below 80 % and the temperature at least +10 °C.

Drying time

Thin coats: Tack-free in approx. 8 hours, final drying depends on the number of treatments. Let the previous coat dry at least 24 hours before the second layer is applied.

Coverage

Rough sawn timber approx. 6 m²/L, planed timber approx. 10 m²/L.

When soaking or immersing timber, porosity and time are decisive:

the consumption is substantially greater than when the paint is applied with brush.

Thinner

Uula Oil Paint Thinner 1166

Cleaning of equipment

Clean the equipment with Uula Universal Thinner or petroleum spirit and rinse with soap and water.

Container sizes

0.9 L, 2.7 L, 9 L

Storage & disposal

Keep in a cool and dry place. Keep out of the reach of children Does not freeze.

Always stir well before use as the pigment settles during storage.

Dry and empty containers can be taken to a refuse dump.

Liquid waste must be taken to a municipal hazardous waste collection point.

Fire classification

Non-flammable.

Caution: Linseed oil on cleaning rags etc. may catch fire by itself. Oily rags and cloths etc. should be burned or rinsed in water before putting into refuse bins.

Instruction for use

Preparations

Brush off dust. Wash dirty surfaces with Uula Washing Agent and mouldy ones with Uula Mould Cleaning Agent. Remove peeling and loose old wood preservative with a wire brush and scraper. Treat the surface with Uula Anti-Mould Agent and let dry thoroughly. Remember to sand new planed surfaces rough to ensure adhesion.

Finishing

Apply 2 coats of Oil of Uula. Let the surface dry in between treatments.

Maintenance treatment on previously treated surfaces must be done using the original or a slightly darker shade.

Impregnation of timber by brush impregnation

Apply 1-4 coats of Uula Wood Oil at 1 hour intervals. Under extreme conditions 1-2 extra treatments are recommended 24 hours after the first treatments at earliest.

Impregnation by immersion impregnation

Immerse the timber in Uula Wood Oil. Let the agent absorb from a few minutes to a few hours, depending on the use. Let excess oil flow.

Smoothen out run-offs by brush. Let dry on top of a grate or laths.

Points to note

*Reserve enough paint for a large surface to avoid potential colour variations in different batches.

*Always stir well before and during use.

*The colour and texture (planed or sawn timber etc.) of the surface to be treated must be taken into consideration when choosing a translucent paint shade.

*A small test is recommended before the actual treatment.

*Paint also cross-sectional surfaces carefully.

*Dense or new planed surface slows absorption of the product and increases drying time.

*It is recommended to roughen a new planed surface before surface treatment to ensure proper absorption.

*Do not apply Uula Wood Oil in rain, direct sunlight or on sun heated surfaces

*New planed surface should be sanded to ensure adhesion or let the wood age for 1-2 years before applying Uula Wood Oil.

*If the surface becomes dirty or mouldy, cleaning or washing the surface should be considered

*More detailed instructions for maintenance and cleaning can be found in our website www.uula.fi

*In case of uncertainty, submit to the manufacturer of the paint or to a competent distributor before starting the painting process.

Information in the technical specification is based on tests and practical experience. All instructions are only indicative and depend, for example, on the texture of the surface, quality, colour and previous treatments. Because we cannot control the use and working conditions of our products we take responsibility only for the quality of the product and guarantee that it is in accordance with the high standards of Uulatote Oy. We do not take responsibility for damage caused by using the product against our instructions or intended use.